

Determination of Vickers hardness  
with low effort  
 $1,961 \text{ N} \leq F < 49,03 \text{ N}$

$F = 1,961 \text{ N}$   
(HV 0,2)

$F = 2,942 \text{ N}$   
(HV 0,5)

$F = 4,903 \text{ N}$   
(HV 1)

$F = 9,807 \text{ N}$   
(HV 2)

$F = 19,61 \text{ N}$   
(HV 3)

$F = 29,42 \text{ N}$   
(HV 3)



VASYL MOSHCHENOK

# Hardness Testing Methods: Brinell, Rockwell, and Vickers

Book 2. Macro, Micro, and Nano  
Range